



REST Journal on Advances in Mechanical Engineering

Vol: 2(1), March 2023

REST Publisher; ISSN: 2583-4800

Website: <http://restpublisher.com/journals/jame/>

DOI: <https://doi.org/10.46632/jame/2/1/4>



Machinability analysis in Drilling Composites and drilling woven GFR/epoxy composites using the SPSS Method

*Chinnasami Sivaji, M. Ramachandran, Vidhya Prasanth

REST Labs, Kaveripattinam, Krishnagiri, Tamil Nadu, India.

*Corresponding author Email: chinnasami@restlabs.in

Abstract. Drilling processes in fiber-reinforced polymer composites Composite structures are essential for assembly and fabrication of parts. The economic impact of rejecting the drilled area, when reaching the assembly stage, it is important to consider the associated loss. Therefore, the motivations in drilling E-Class Fiber Reinforced Epoxy (GFRE) composites, this explains cutting conditions on torque and wear Feed, speed and pre-drill wear values. Four feeds (0.056, 0.112, 0.22, 0.315, 0.45 mm/rev) and three speeds (6.41, 12.71, 20.25, 32.03, and 50.63 m/min) and five pre-drill wear values and four artificially introduced wears) were used. Values; $W = 7, 19, 26, 34$ All samples are 8 mm diameter holes Drilled using a cemented carbide drill bit. Current In work, Multi-linear Regression models were used were used, Parameters of mechanical properties are related to: Thrust, torsion, peel-up, delamination, push-out delamination, Drill wear and machining parameters such as surface roughness before: feed and speed. Perforated model has high resolution; Scanning is done using flatbed color scanner, then to estimate the delamination factor, Image analysis was performed using Corel DRAW software. Multi-variable regression analysis significant coefficients of each variable, contribution is made to promotion and elimination. Laminate thickness on torque and displacement factors the results illustrate that there are significant effects. Cronbach's alpha value for the model is 0.924.

Evaluation preference: Speed, Wear, Feed, Ft, T, Del.Peel, Del.Push and Ra.

Results: the Cronbach's Alpha Reliability result. The overall Cronbach's Alpha value for the model is 0.924 which indicates 92% reliability. From the literature review, the above 50% Cronbach's Alpha value model can be considered for analysis

Keywords: Speed, Wear, Feed, Del. Peel and Del. Push.

1. INTRODUCTION

Currently polymeric composites are gradually in some industrial applications Used to transform metals and alloys, this is a positive development. For example, some metal components of aircraft replaced by carbon/epoxy composite components. In marine applications the use of fiber/polymer composites has also been explored; many metal parts on ships are replaced by fiber/polymer composites. A common machining practice is metal matrix composites Machining requires appropriate tools. On the other hand, including carbon fiber and glass fiber composites synthetic fiber composites, Due to the inertness of fibers, Due to extreme erection and impotence due to impotence, they pose a significant endurance, Challenge in terms of material removal rate and propulsion. Force, shear force, Ra (hardness average) and removal rate. They have anisotropic and heterogeneous properties. Also, because the abrasive properties of synthetic fibers are poor resulting in surface coating and Rapid tool wear. To ensure the efficiency of the process, cutting parameters and tooling correctly it is necessary to be selected. However, in the last few years, many researchers have shown the effect of machining parameters, for example If, fiber orientation, such as hole diameter, speed and feed It is said to have a significant effect on the machinability of materials. However, natural fiber-reinforced with machining force, cutting stress, tool life, cutting force and power, Material removal rate, ding force, less work has been done on the machining of composite materials such as raw and tool wear. Performed on mechanical properties of synthetic materials. Synthetic fibers are important for machine tools and machinery, it is now widely recognized that some specific substances can cause damage: Basically, a cutting tool consists of two main parts, that is, lateral wear on the lateral face of the tool and groove. Wear on the face of the tool rack. Both Davie and Reiss advanced drilling parameters and for better wear resistance keep the carbide inserts. Hence better drilling performance than HSS drills It was by increasing the lateral wear of the drill bit as the lamination factor increases and the spin speed increases the results show that of drill wear the effect is significant. Bhattacharya and Horrigan's results Kevlar composites in drilling thrust force with Number of holes drilled and surface roughness gradually and the torque decreases slightly. Rawat and Attica were motivated by drill Applies to Controllable process variables and tool wear and final overall

quality and investigated the effect on hole quality. (Delamination, geometrical errors and surface finish) have a strong correlation. Finally, by monitoring shear forces Tool replacement strategy they decided to create. In this work, at various cutting positions front wear on mechanical properties parameters was investigated. Mechanical properties parameters thrust force, torque, includes peel-up and push-out delamination are classified are characterized by of drilled holes surface roughness. Linear regression models for wear and tear on Mach incapacity parameters. For the statistical analysis, we used SPSS software version 16.

2. WOVEN GFR/EPOXY COMPOSITES

Different thicknesses in drilling GFRE composite speed and thrust force, this section presents the effects of feed on torsion and delamination. of induced delamination films in perforated GFRE composites Examples are illustrated for different feed and speed of 800 rpm. Epson "V370, 4800 x 9600 dpi" high resolution images Scans are made using a flatbed color scanner model. 800 rpm and a speed of 0.1 mm/rev for a sample of 7.7 mm thickness. During drilling of woven GFRE composite Variation of thrust force with respect to displacement and time. Data was recorded with frequency = 1000 Hz and filtered at 100 data points. E-glass woven Roving fiber reinforced epoxy composite laminates presented earlier Manufactured using a hand lay-up process. Be careful when cutting and laying woven fiberglass panels. Perfect for all layers to confirm the angles Cut through warp and weft threads. Laminates are 25 layers and 8.3 mm thick [0] has 25 layers. According to ASTM D3171-99 Fiber Volume Fraction (If). The use of welding technique was determined experimentally. The average value of If is 35%. Woven using universal test machine A series of ASTM tests on GFRE composites carried out. In tension and bearing tests The cross-sectional speed of the loading member was 1.27 mm/min. Monitoring of load and displacement during testing, Draw the relationship between them in real time The test machine is connected to a personal computer. Radial drilling machine "StankoImport (Moskva - SSSP)" 21 spindle rotation speed (20 to 2000 rpm) and 12 longitudinal feeds (0.056 to 2.5 mm/rev) in GFRE composites Drilling procedures were carried out. Five spindle speeds (6.41, 12.710, 20.25, 32.03, 50.64m/min) and five feeds (0.056, 0.112, 0.22, 0.315, 0.45 mm) of .50 were used. The point angle is 120 and the flute angle is 30 with different diameters (/8 and /13 mm). Thrust force in drilling GFRE composites, Effect of cutting removal and surface roughness (/8 and /13 mm) parameters was investigated using two exercises. Bearing for 8 mm diameter holes. Parameter in strength the effect of cutting was investigated. 120-point angle and 30 flute angles with cemented carbide twist drill Machining processes are carried out in the present work. Actual in machining processes Drill wear is due to variation in normal rake angle, by grinding machine Difficult to produce but also for the variation of the cutting speed. In the present work, GFRP composites (Cutting Edge, Chisel Edge, Flange and Flute) At the drill point in drilling, filled with silicon particles to simulate real wear mechanisms by drilling GFRP Pre-drilling dressing is achieved. Drill point wear Abrasions to accelerate. Weight loss was periodically recorded up to $W = 7 \text{ } 104 \text{ g}$. 25 holes in GFRE compounds A drill was used for machining. Silicon particles up to $W = 19 \text{ } 104 \text{ g}$ in the same drill Filled GFRP Drilling A pre-block is introduced, It was used to drill 25 holes with different cut positions. Drilling of GFRP filled with silicon particles up to $W = 19 \text{ } 104 \text{ g}$ the same drill A pre-block is introduced; it was used to drill 25 holes with different cut positions. The wear values before the drill are equal to $w = 26 \text{ } 104$ and $34 \text{ } 104 \text{ g}$ this process was repeated. A StankoImport (Moskva-SSSP) radial drill machine with 21 spindle rotation speeds (20 to 2000 rpm) and 12 longitudinal feeds (0.056 to 2.5 mm/rev) were used to drill the samples. All models diameter 8 mm, holes Drilled using a cemented carbide drill. Five spin Velocity ($V = 6.41, 12.71, 20.25, 32.03, \text{ and } 50.63 \text{ m/min}$), ($f = 0.056, 0.112, 0.22, 0.315, 0.315/0$) in five artificially introduced exercises. Pre-wear values; $W = 7, 19, 26, 34 \text{ g } 104$). Using "AutoCAD method". Surface removal was measured; it is semi-transparent Suitable for composite materials. On technical setup and measurement procedures The details were previously published by Kashaya. Delamination size is Maximum Damage Rates (RAM) and drilled hole radius ($R = 4 \text{ mm}$). Between surface roughness (R_a) Perforated hole wall Defined differently "Rank Taylor Hobson Sardonis 3+" Surface roughness was measured using a measuring instrument. T-off and travel length values respectively 0.8 mm and 4 mm are taken. Surface roughness value of each sample Arithmetic mean value of three surface roughness measurements, they are divided into three different levels from 60-90 along the circumference of the pore wall. Using a JT-off and travel The length values are respectively taken as 0.8 mm and 4 mm. Surface roughness value of each sample is the arithmetic mean value of three surface roughness measurements, J.S.M-T100 Scanning Electron Microscope v Drill Front Wear and at different values of shear conditions. Matrix Deformation in Drilling GFRE Composites and photos illustrate hardening process.

3. RESULT AND DISCUSSION

Table 1 Descriptive Statistical Analysis of Speed, Wear, Feed, Ft, T, Del.Peel, Del.Push, Raw N, Range, Minimum, Maximum, Mean, Standard Deviation Variance curve values are given.

TABLE 1. Descriptive Statistics

	N	Range	Minimum	Maximum	Mean	Std. Deviation	Variance	Skewness
Speed	125	44.23	6.41	50.64	24.4080	15.71080	246.829	.581
Wear	125	34	0	34	17.20	12.401	153.790	-.077
Feed	125	.3940	.0560	.4500	.230600	.1419359	.020	.299
Ft	125	9.6316E2	27.6400	990.8000	3.750758E2	238.0707628	5.668E4	.607
T	125	.8610	.1500	1.0110	.657520	.2355482	.055	-.384
Del. Peel	125	1.3160	.4840	1.8000	1.265696E0	.2900961	.084	-.633
Del. Push	125	2.4770	1.1510	3.6280	2.573824E0	.5710201	.326	-.784
Ra	125	7.1600	2.2900	9.4500	5.996120E0	1.7911298	3.208	-.454
Valid N (listwise)	125							

TABLE 2. Frequency Statistics

		Speed	Wear	Feed	Ft	T	Del.Peel	Del.Push	Ra
Std. Error of Mean		1.40522	1.109	.0126951	2.1293696E1	.0210681	.0259470	.0510736	.1602035
Mode		6.41 ^a	0 ^a	.0560 ^a	2.7640E1 ^a	.8520	1.1000 ^a	2.2010 ^a	2.9500 ^a
Sum		3051.00	2150	28.8250	4.6884E4	82.1900	1.5821E2	321.7280	7.4951E2
Percentiles	25	12.7100	7.00	.112000	2.017250E2	.445500	1.080000E0	2.272000	5.185000E0
	50	20.2500	19.00	.220000	3.320200E2	.724000	1.322000E0	2.738000	6.190000E0
	75	32.0300	26.00	.315000	5.255150E2	.873500	1.504000E0	2.967000	7.460000E0

Table 2 Frequency Statistics Analysis of Speed, Wear, Feed, Ft, T, Del.Peel, Del.Push, Raw N, Range, Minimum, Maximum, Mean, Standard Deviation Variance curve values are given.

TABLE 3. Reliability Statistics

Based on Cronbach's alpha standardized items	N of Items
.924	5

Table 3 shows the Cronbach's Alpha Reliability result. The overall Cronbach's Alpha value for the model is 0.924 which indicates 92% reliability. From the literature review, the above 50% Cronbach's Alpha value model can be considered for analysis

TABLE 4. Sample summary

Model	R	R Square	Adjusted R Square	Sum of Squares	df	F	Sig.
1	.919 ^a	.844	.840	95.2265139	3	218.010	.000 ^a
2	.937 ^a	.877	.874	12.034	3	287.798	.000 ^a
3	.845 ^a	.714	.707	10.449	3	100.627	.000 ^a
4	.887 ^a	.788	.782	31.846	3	149.602	.000 ^a
5	.925 ^a	.856	.853	340.676	3	240.497	.000 ^a
a. Predictors: (Constant), Feed, Wear, Speed							

Table 4 shows the result of R, R squared, adjusted R squared, sum of squares, df, F, significance. The overall R squared value for the model is above 0.8, so this is reliable data. From the literature review, R value above 0.5 can be considered to analyze the model. The sum of squares value for the model is greater than 10.0, so this is reliability data. From the literature review, the value of squares above 10 can be considered to analyze the model. The overall F value for the model is above 100.0, so this is reliability data. From the literature review, a value above 10 can be considered to analyze the model. The overall identity value for the model is 0.000, so this is reliability data. From the literature review, a value less than 0.5 can be considered to analyze the model.

Table 5 shows the correlation between the stimulus parameters for speed. Line plotting has the highest value of .245 so it has a high correlation with feet and the lowest value is -0.261 so it has a low correlation with Del.peel. Next is the correlation between Wear stimulus parameters. Line plotting maximum value is 0.905 so it has high correlation with Ra and minimum value is 0.000 so it has low correlation with two parameters Feed and Speed. Next the correlation between the stimulus parameters for Feed. Line plotting has the highest value of 0.855 so it has a high correlation with Ra and the

lowest value is -0.261 so it has a low correlation with Wear and Speed. Next the correlation between the stimulus parameters for Ft. Line plotting has the highest value of 0.766so it has a high correlation with T and the lowest value is 0.245 so it has a low correlation with Speed.

TABLE 5. Correlations

	Speed	Wear	Feed	Ft	T	Del.Peel	Del.Push	Ra
Speed	1	.000	.000	.245	-.056	-.261	.040	.093
Wear	.000	1	.000	.666	.379	.654	.419	.905
Feed	.000	.000	1	.583	.855	.467	.781	.170
Ft	.245	.666	.583	1	.766	.725	.729	.758
T	-.056	.379	.855	.766	1	.714	.882	.498
Del.Peel	-.261	.654	.467	.725	.714	1	.681	.764
Del.Push	.040	.419	.781	.729	.882	.681	1	.555
Ra	.093	.905	.170	.758	.498	.764	.555	1

Next the correlation between the stimulus parameters for T. Line plotting has the highest value of 0.245 so it has a high correlation with Del.Push and the lowest value is -0.056so it has a low correlation with Speed. Next the correlation between the stimulus parameters for Del.peel. Line plotting has the highest value of 0.764so it has a high correlation with Ra and the lowest value is -0.261 so it has a low correlation with Speed. Next the correlation between the stimulus parameters for Del.Push. Line plotting has the highest value of 0.882so it has a high correlation with T and the lowest value is 0.040so it has a low correlation with Speed. Next the correlation between the stimulus parameters for Ra. Line plotting has the highest value of 0.905so it has a high correlation with Wear and the lowest value is -0.261 so it has a low correlation with Speed.




FIGURE 1. Frequency for Ft histogram plots

Figure 1 shows a histogram plot for feet from the figure where it can be clearly seen that the data is slightly skewed to the left due to high values for 0.000-400, while all other values are under the normal curve, the sample substantially follows a normal distribution.

Figure 2 shows a histogram plot for legs where it is clear that the data is slightly skewed to the right due to high values for 0.8000-10000, while all other values are under the normal curve, the pattern follows substantially.




FIGURE 2. Frequency for T histogram plots




FIGURE 3. Frequency for Del.peel histogram plots

Figure 3 shows the histogram plot for Del.peel as the data is skewed due to values for 0.5000-2.0000, while all other values are under the normal curve, the sample is significant. follows a normal distribution.




FIGURE 4. Frequency for Del.Push histogram plots

Figure 4 shows the histogram plot for Del.Push as the data is skewed due to values for 1.0000-4.0000, while all other values are under the normal curve, the sample is significant. Follows a normal distribution.




FIGURE 5. Frequency for Ra histogram plots

Figure 5 shows the histogram plot for Del.Push as the data is skewed due to values for 2.0000-10.0000, while all other values are under the normal curve, the sample is significant. Follows a normal distribution.

4. CONCLUSION

On mechanical properties parameters (push force, torsion, In drilling GFRE composites peel-off and push-out delamination and surface roughness). Drill front wear and mechanical conditions (feed and speed) to evaluate the effect. A trial investigation was carried out. When driving force behavior drilling operation the results show that the drill front is heavily affected by to wear This effect becomes very significant higher speeds feeds, this Increases Peel-up and push-out delamination. There is increasing drill pre-wear results in increased thrust force leading to destruction of At matrix and ply interfaces microcracking, This makes the surface rough. Additionally, high speed Wear before drilling and drilling due to the generated temperatures causing high surface roughness; it has low thermal conductivity and GFRE composites Aided by low transition temperatures. Cronbach's alpha value for the model is 0.924. Both of histogram plots normal curve.

REFERENCES

- [1]. Shalwan, Abdullah, Talal Alsaeed, and Belal Yousif. "Machinability of Polymeric Composites and Future Reinforcements—A Review." *Journal of Materials Science and Chemical Engineering* 10, no. 5 (2022): 40-72.
- [2]. Rathor, Ketan, Anshul Mandawat, Kartik A. Pandya, Bhanu Teja, Falak Khan, and Zoheib Tufail Khan. "Management of Shipment Content using Novel Practices of Supply Chain Management and Big Data Analytics." In *2022 International Conference on Augmented Intelligence and Sustainable Systems (ICAISS)*, pp. 884-887. IEEE, 2022.
- [3]. Gutu, Birhanu, Genelegese, Nigussie Fikadu, Birhanu Kumela, Firafan Shuma, Wakgari Mosisa, Zelalem Regassa et al. "Assessment of preventive behavior and associated factors towards COVID-19 in Qellam Wallaga Zone, Oromia, Ethiopia: A community-based cross-sectional study." *PloS one* 16, no. 4 (2021): e0251062.
- [4]. Chakrabarti, P., B. Bhuyan, A. Chowdhuri, and C. Bhunia. "A novel approach towards realizing optimum data transfer and Automatic Variable Key (AVK) in cryptography." *IJCSNS* 8, no. 5 (2008): 241.
- [5]. Khashaba, U. A., I. A. El-Sonbaty, A. I. Selmy, and A. A. Megahed. "Machinability analysis in drilling woven GFR/epoxy composites: Part I—Effect of machining parameters." *Composites Part A: Applied Science and Manufacturing* 41, no. 3 (2010): 391-400.
- [6]. Rathor, Ketan, Sushant Lenka, Kartik A. Pandya, B. S. Gokulakrishna, Susheel Sriram Ananthan, and Zoheib Tufail Khan. "A Detailed View on industrial Safety and Health Analytics using Machine Learning Hybrid Ensemble Techniques." In *2022 International Conference on Edge Computing and Applications (ICECAA)*, pp. 1166-1169. IEEE, 2022.
- [7]. Pathan, M. V., S. A. Ponnusami, J. Pathan, R. Pitongsawat, B. Erice, N. Petrinic, and V. L. Tagarielli. "Predictions of the mechanical properties of unidirectional fibre composites by supervised machine learning." *Scientific reports* 9, no. 1 (2019): 1-10.
- [8]. Jisha, L., P. Jayaprabha, S. Gnanawel, K. Gowtham Kumar, and P. Kogila. "Assessment of the Prevalence of Febrile Seizure and Associated Factors among Children: A Retrospective Study." *EXECUTIVE EDITOR* 11, no. 03 (2020): 3179.
- [9]. Chittora, Pankaj, Sandeep Chaurasia, Prasun Chakrabarti, Gaurav Kumawat, Tulika Chakrabarti, Zbigniew Leonowicz, Michał Jasiński et al. "Prediction of chronic kidney disease—a machine learning perspective." *IEEE Access* 9 (2021): 17312-17334.
- [10]. Khashaba, U. A., I. A. El-Sonbaty, A. I. Selmy, and A. A. Megahed. "Machinability analysis in drilling woven GFR/epoxy composites: Part I—Effect of machining parameters." *Composites Part A: Applied Science and Manufacturing* 41, no. 3 (2010): 391-400.
- [11]. Sharma, Akhilesh Kumar, Gaurav Aggarwal, Sachit Bhardwaj, Prasun Chakrabarti, Tulika Chakrabarti, Jemal H. Abawajy, Siddhartha Bhattacharyya, Richa Mishra, Anirban Das, and Hairulnizam Mahdin. "Classification of Indian classical music with time-series matching deep learning approach." *IEEE Access* 9 (2021): 102041-102052.
- [12]. Sacco, Christopher, Anis Baz Radwan, Andrew Anderson, Ramy Harik, and Elizabeth Gregory. "Machine learning in composites manufacturing: A case study of Automated Fiber Placement inspection." *Composite Structures* 250 (2020): 112514.
- [13]. Nigatu, A., and D. B. Demissie. "Knowledge, attitude and practice on voluntary blood donation and associated factors among Ambo University Regular Students, Ambo Town, Ethiopia." *J Community Med Health Educ* 4, no. 5 (2014): 6-6.
- [14]. Khashaba, U. A., I. A. El-Sonbaty, A. I. Selmy, and A. A. Megahed. "Drilling analysis of woven glass fiber-reinforced/epoxy composites." *Journal of composite materials* 47, no. 2 (2013): 191-205.
- [15]. Chowdhury, Sayan, Tulika Mukherjee, Somenath Roy Chowdhury, Souvik Sengupta, Sibabrata Mukhopadhyay, Parasuraman Jaisankar, and Hemanta K. Majumder. "Disuccinyl betulin triggers metacaspase-dependent endonuclease G-mediated cell death in unicellular protozoan parasite *Leishmania donovani*." *Antimicrobial agents and chemotherapy* 58, no. 4 (2014): 2186-2201.
- [16]. Marani, Afshin, and Moncef L. Nehdi. "Machine learning prediction of compressive strength for phase change materials integrated cementitious composites." *Construction and Building Materials* 265 (2020): 120286.
- [17]. Wahlang, Imayanmosha, Arnab Kumar Maji, Goutam Saha, Prasun Chakrabarti, Michał Jasinski, Zbigniew Leonowicz, and Elzbieta Jasinska. "Deep Learning methods for classification of certain abnormalities in Echocardiography." *Electronics* 10, no. 4 (2021): 495.
- [18]. Chhipa, Abrar Ahmed, Vinod Kumar, Raghuveer Raj Joshi, Prasun Chakrabarti, Michał Jasinski, Alessandro Burgio, Zbigniew Leonowicz, Elzbieta Jasinska, Rajkumar Soni, and Tulika Chakrabarti. "Adaptive neuro-fuzzy inference system-based maximum power tracking controller for variable speed WECS." *Energies* 14, no. 19 (2021): 6275.

- [19]. Rao, B. Srinivasa, R. Rudramoorthy, S. Srinivas, and B. Nageswara Rao. "Effect of drilling induced damage on notched tensile and pin bearing strengths of woven GFR-epoxy composites." *Materials Science and Engineering: A* 472, no. 1-2 (2008): 347-352.
- [20]. Rakshit, Srabanti, Labanya Mandal, Bikas Chandra Pal, Jayashree Bagchi, Nabendu Biswas, Jaydeep Chaudhuri, Avik Acharya Chowdhury et al. "Involvement of ROS in chlorogenic acid-induced apoptosis of Bcr-Abl+ CML cells." *Biochemical pharmacology* 80, no. 11 (2010): 1662-1675.
- [21]. Aswini, S., S. Tharaniya, RJ Joey Persul, B. Avinash Lingam, and P. Kogila. "Assessment of Knowledge, Attitude and Practice on Immunization among Primi Mothers of Children." *Indian Journal of Public Health Research & Development* 11, no. 3 (2020): 583-587.
- [22]. Sharma, Akhilesh Kumar, Gaurav Aggarwal, Sachit Bhardwaj, Prasun Chakrabarti, Tulika Chakrabarti, Jemal H. Abawajy, Siddhartha Bhattacharyya, Richa Mishra, Anirban Das, and Hairulnizam Mahdin. "Classification of Indian classical music with time-series matching deep learning approach." *IEEE Access* 9 (2021): 102041-102052.
- [23]. Cho, Sung-Kyum, Hyun-Jun Kim, and Seung-Hwan Chang. "The application of polymer composites to the table-top machine tool components for higher stiffness and reduced weight." *Composite Structures* 93, no. 2 (2011): 492-501.
- [24]. Chowdhury, Sayan, Tulika Mukherjee, Rupkatha Mukhopadhyay, Budhaditya Mukherjee, Souvik Sengupta, Sharmila Chattopadhyay, Parasuraman Jaisankar, Syamal Roy, and Hemanta K. Majumder. "The lignan niranthin poisons *Leishmania donovani* topoisomerase IB and favours a Th1 immune response in mice." *EMBO Molecular Medicine* 4, no. 10 (2012): 1126-1143.
- [25]. Parameshwaranpillai, T., P. R. Lakshminarayanan, and B. Nageswara Rao. "Taguchi's Approach to Examine the Effect of Drilling Induced Damage on the Notched Tensile Strength of Woven GFR-epoxy Composites." *Advanced Composite Materials* 20, no. 3 (2011): 261-275.
- [26]. Huang, J. S., J. X. Liew, and K. M. Liew. "Data-driven machine learning approach for exploring and assessing mechanical properties of carbon nanotube-reinforced cement composites." *Composite Structures* 267 (2021): 113917.
- [27]. Chowdhury, Sayan, Tulika Mukherjee, Souvik Sengupta, Somenath Roy Chowdhury, Sibabrata Mukhopadhyay, and Hemanta K. Majumder. "Novel betulin derivatives as antileishmanial agents with mode of action targeting type IB DNA topoisomerase." *Molecular pharmacology* 80, no. 4 (2011): 694-703.
- [28]. Matos, Miguel AS, Silvestre T. Pinho, and Vito L. Tagarielli. "Application of machine learning to predict the multiaxial strain-sensing response of CNT-polymer composites." *Carbon* 146 (2019): 265-275.
- [29]. Chakrabarti, Prasun, Tulika Chakrabarti, Siddhant Bane, Biswajit Satpathy, Indranil SenGupta, and Jonathan Andrew Ware. "Analysis of Strategic Market Management in Light of Stochastic Processes, Recurrence Relation, Abelian Group and Expectation." In *Advances in Artificial Intelligence and Data Engineering: Select Proceedings of AIDE 2019*, pp. 701-710. Springer Singapore, 2021.
- [30]. El-Sonbaty, I., U. A. Khashaba, and T. Machaly. "Factors affecting the machinability of GFR/epoxy composites." *Composite structures* 63, no. 3-4 (2004): 329-338.
- [31]. Chittora, Pankaj, Sandeep Chaurasia, Prasun Chakrabarti, Gaurav Kumawat, Tulika Chakrabarti, Zbigniew Leonowicz, Michał Jasiński et al. "Prediction of chronic kidney disease-a machine learning perspective." *IEEE Access* 9 (2021): 17312-17334.
- [32]. Muir, C., B. Swaminathan, A. S. Almansour, K. Sevens, C. Smith, M. Presby, J. D. Kiser, T. M. Pollock, and S. Daly. "Damage mechanism identification in composites via machine learning and acoustic emission." *npj Computational Materials* 7, no. 1 (2021): 95.
- [33]. Das, Tania, Kumar Singha Roy, Tulika Chakrabarti, Sibabrata Mukhopadhyay, and Susanta Roychoudhury. "Withaferin A modulates the Spindle Assembly Checkpoint by degradation of Mad2-Cdc20 complex in colorectal cancer cell lines." *Biochemical pharmacology* 91, no. 1 (2014): 31-39.
- [34]. Khashaba, U. A., I. A. El-Sonbaty, A. I. Selmy, and A. A. Megahed. "Machinability analysis in drilling woven GFR/epoxy composites: Part I-Effect of machining parameters." *Composites Part A: Applied Science and Manufacturing* 41, no. 3 (2010): 391-400.
- [35]. Hung, Bui Thanh, and Prasun Chakrabarti. "Parking lot occupancy detection using hybrid deep learning CNN-LSTM approach." In *Proceedings of 2nd International Conference on Artificial Intelligence: Advances and Applications: ICAIAA 2021*, pp. 501-509. Singapore: Springer Nature Singapore, 2022.
- [36]. Khashaba, Usama A., Mohamed S. Abd-Elwahed, Khaled I. Ahmed, Ismail Najjar, Ammar Melaihari, and Mohamed A. Eltaher. "Analysis of the machinability of GFRE composites in drilling processes." *Steel Compos. Struct* 36, no. 4 (2020): 417-426.
- [37]. Chakrabarti, Tulika, Sibabrata Mukhopadhyay, Prasun Chakrabarti, Gholamreza Hatam, and Mohammad Nami. "Phenyl Ethanoid Glycoside from the Bark of *Oroxylum indicum* Vent: a Potential Inhibitor of DNA Topoisomerase IB of *Leishmania donovani*." *Journal of Advanced Medical Sciences and Applied Technologies* (2021).
- [38]. Marani, Afshin, and Moncef L. Nehdi. "Machine learning prediction of compressive strength for phase change materials integrated cementitious composites." *Construction and Building Materials* 265 (2020): 120286.
- [39]. Jin, Xue-Bo, Zhong-Yao Wang, Wen-Tao Gong, Jian-Lei Kong, Yu-Ting Bai, Ting-Li Su, Hui-Jun Ma, and Prasun Chakrabarti. "Variational bayesian network with information interpretability filtering for air quality forecasting." *Mathematics* 11, no. 4 (2023): 837.
- [40]. Yazman, Şakir. "The effects of back-up on drilling machinability of filament wound GFRP composite pipes: Mechanical characterization and drilling tests." *Journal of Manufacturing Processes* 68 (2021): 1535-1552.
- [41]. Kanti Das, Sreemoy, G. S. Chakraborty, Tulika Chakrabarti, Prasun Chakrabarti, Mohammad Javad Gholamzadeh, and Mohammad Nami. "Evaluation of nootropic activity of standardized *Epipremnum aureum* extract against scopolamine-induced amnesia in experimental animals." *Journal of Advanced Medical Sciences and Applied Technologies* 6, no. 1 (2021): 64-71.

- [42]. Khashaba, U. A., A. I. Selmy, I. A. El-Sonbaty, and M. Megahed. "Behavior of notched and unnotched $[0/\pm 30/\pm 60/90]$ s GFR/EPOXY composites under static and fatigue loads." *Composite structures* 81, no. 4 (2007): 606-613.
- [43]. Gupta, Harsh Vardhan, Vivek Vardhan Gupta, Amanlo Kaur, Ruku Singla, Neha Chitkara, Krushnan V. Bajaj, and H. C. L. Rawat. "Comparison between the analgesic effect of two techniques on the level of pain perception during venipuncture in children up to 7 years of age: A quasi-experimental study." *Journal of clinical and diagnostic research: JCDR* 8, no. 8 (2014): PC01.
- [44]. Zobeiry, Navid, Johannes Reiner, and Reza Vaziri. "Theory-guided machine learning for damage characterization of composites." *Composite Structures* 246 (2020): 112407.
- [45]. Solanki, Yogendra Singh, Prasun Chakrabarti, Michal Jasinski, Zbigniew Leonowicz, Vadim Bolshev, Alexander Vinogradov, Elzbieta Jasinska, Radomir Gono, and Mohammad Nami. "A hybrid supervised machine learning classifier system for breast cancer prognosis using feature selection and data imbalance handling approaches." *Electronics* 10, no. 6 (2021): 699.
- [46]. Koumoulos, Elias, George Konstantopoulos, and Costas Charitidis. "Applying machine learning to nanoindentation data of (nano-) enhanced composites." *Fibers* 8, no. 1 (2019): 3.
- [47]. Rathor, Ketan, Keyur Patil, Mandiga Sahasra Sai Tarun, Shashwat Nikam, Devanshi Patel, and Sasanapuri Ranjit. "A Novel and Efficient Method to Detect the Face Coverings to Ensure the Safety using Comparison Analysis." In *2022 International Conference on Edge Computing and Applications (ICECAA)*, pp. 1664-1667. IEEE, 2022.
- [48]. Manjunath, C. R., Ketan Rathor, Nandini Kulkarni, Prashant Pandurang Patil, Manoj S. Patil, and Jasdeep Singh. "Cloud Based DDOS Attack Detection Using Machine Learning Architectures: Understanding the Potential for Scientific Applications." *International Journal of Intelligent Systems and Applications in Engineering* 10, no. 2s (2022): 268-271
- [49]. Sharma, Akhilesh Kumar, Shamik Tiwari, Gaurav Aggarwal, Nitika Goenka, Anil Kumar, Prasun Chakrabarti, Tulika Chakrabarti, Radomir Gono, Zbigniew Leonowicz, and Michał Jasiński. "Dermatologist-level classification of skin cancer using cascaded ensembling of convolutional neural network and handcrafted features based deep neural network." *IEEE Access* 10 (2022): 17920-17932.
- [50]. Kumar, Ashish, Ketan Rathor, Snehit Vaddi, Devanshi Patel, Preethi Vanjarapu, and Manichandra Maddi. "ECG Based Early Heart Attack Prediction Using Neural Networks." In *2022 3rd International Conference on Electronics and Sustainable Communication Systems (ICESC)*, pp. 1080-1083. IEEE, 2022.
- [51]. Kropce, J., A. Ghani Olabi, D. Goričanec, and S. Božičnik. "Assessment of Optimal Drilling Parameter for Bamboo Filler Reinforced Epoxy Composite." In *10TH International Conference on Sustainable Energy and Environmental Protection Mechanical Engineering*, p. 101. 2017.
- [52]. Taniuchi, Mami, Michael Famulare, Khalequ Zaman, Md Jashim Uddin, Alexander M. Upfill-Brown, Tahmina Ahmed, Parimalendu Saha et al. "Community transmission of type 2 poliovirus after cessation of trivalent oral polio vaccine in Bangladesh: an open-label cluster-randomised trial and modelling study." *The Lancet Infectious Diseases* 17, no. 10 (2017): 1069-1079.
- [53]. Sun, Junbo, Yongzhi Ma, Jianxin Li, Junfei Zhang, Zhenhua Ren, and Xiangyu Wang. "Machine learning-aided design and prediction of cementitious composites containing graphite and slag powder." *Journal of Building Engineering* 43 (2021): 102544.